Technical data sheet



Sam Acrylic Sealer Coat

Product description.

A single pack, non-chalking, non-yellowing, acrylic based primer.

Characteristics

- Excellent priming coat for concrete.
- Designed for marine and Industrial Environment
- Designed for Interior and Exterior use.
- Fast Dry properties.
- Excellent workability.

Physical properties.

Colour Transparent.

Texture Gloss

Mixing and application Information

Number of components One

Specific gravity Approx. 1.1 g/ml

Volume solids 40±2% Tested acc. ASTM D 2369

VOC Approx. 450 g/liter

Flashpoint >25°C

spray Airless spray

Pressure at nozzle: 120 -150 bar. Nozzle size: 0.38 - 0.53 mm.

Spray angle: 40 - 80 degrees.

Thinning Ratio: 0 - 5%.
Convention Air spray
Thinning Ratio: 0 - 5%.

Brush Recommended.

Thinning Ratio: 0 - 5%

Roller Recommended.

Thinning Ratio: 0 - 5%. SAM Thinner No. 3

Thinner/Cleaner SAM Thinner No. 3

Recommended film thickness range

Dry film thickness per coat (µm)	30 – 50 μm	ASTM D1186
Wet film thickness per coat (µm)	60 – 100 μm	ASTM D1212
Theoretical spreading rate (m2/L)	16.6– 5 m²/L	

Technical data sheet



Sam Acrylic Sealer Coat

Surface Preparation

Concrete substrates

- Surfaces shall be treated inaccordance with SSPC SP13/NACE NO 6 /ASTM D4258 -05.
- Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, and other foreign material to ensure adequate adhesion,
- As a general rule the concrete must be stayed to full cure (28days) before any application of flooring paint system.

Coated substrates

- Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, and other foreign material to ensure adequate adhesion.
- Roughen the old coated surface to ensure coating adhesion.

•

Drying and recoating information

Substrate tem	perature	10°C	23°C	30°C	
Touch dry		2 Hours	1 Hour	30 min	
Dry to handle		8 Hours	4 Hours	2 Hours	ASTM D 1640
Full cure		10 Days	7 Days	5 Days	
Dry to recoat	Min.	24 Hours	12 Hours	8 Hours	
	Max	Indefinite	Indefinite	Indefinite	

The drying and curing periods are established by subjecting the product to controlled temperatures and a relative humidity level that does not exceed 85%, and at average DFT range for the product.

Application conditions

- Avoid the formation of moisture on the surface, it is recommended that the temperature of the substrate remains at least 3°C higher than the dew point of the surrounding air, during painting process and until hard dry of the paint. It is important to take measurements of the temperature and relative humidity in the area surrounding the substrate according to ISO 8502-4.
- It is recommended to not exceed the surface temperature of approximately 45°C, as this can lead to the formation of dry-spray, pinholes, and sagging.
- For optimal results, it is important to mix the product thoroughly.
- To achieve the best results, it is advised to follow the product's TDS recommendations for thinning. Over-thinning the product can cause sagging and may also result in a weaker paint film
- When working in small, cramped, confined spaces, it is important to ensure sufficient ventilation during both application and drying time.
- It is important to monitor the temperature of the paint, as it can impact its viscosity. To achieve
 the desired film thickness, it may be necessary to control thinning in order to reach the
 appropriate viscosity, for additional information, please get in touch with your Local SAMCO
 office.

Technical data sheet



Sam Acrylic Sealer Coat

Safety Precautions

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes.
- Avoid inhalation of spray mist, it is important to take appropriate precautions. Skin contact should also be avoided, and any spills should be promptly cleaned up using soap, water, and a suitable cleanser. If the product comes into contact with the eyes, they should be thoroughly flushed with water and medical attention should be sought immediately.
- To ensure safe handling and use, please follow the guidelines below:
 - Wear appropriate personal protective equipment, such as gloves, eye protection, and respiratory protection, when handling or using this product.
 - Avoid direct skin contact and inhalation of dust, mist, or vapor.
 - If skin contact occurs, immediately wash the affected area with soap and water.
 - If the product comes into contact with the eyes, flush them thoroughly with water and seek medical attention immediately.
 - Use this product in a well-ventilated area to minimize the risk of inhalation.
 - Store the product in a cool, dry place, away from sources of heat or ignition.
 - Keep the product out of reach of children and animals.
 - Follow all applicable regulations and guidelines for handling, transportation, and disposal of this product.

Storage and shelf life

Ensure compliance with national regulations, proper storage guidelines must be followed for the product. The cans should be stored in a well-ventilated area that is dry, cool, and kept away from any heat or ignition sources. It is important to ensure that the cans are tightly closed at all times to maintain safety.

Disclaimer

All information in this document has been prepared to the best of SAMCO's knowledge, based on laboratory testing and practical experience to ensure good workmanship. However, the responsibility for executing the work stays with the applicator/contractor/sub-contractor. SAMCO products are used under conditions beyond SAMCO's control. Users should always consult SAMCO for specific guidance on the general suitability of this product for their needs and specific application practices. SAMCO reserves the right to change the given data without further notice.