

Product description.

A high-build, Two-component, Polyamine-cured epoxy coat with excellent anticorrosive properties.

Characteristics

- Good abrasion and impact resistance.
- Used for new construction and maintenance applications
- Surface tolerant and good adhesion to St3 prepared steel substrates.
- Compatible with most aged coatings with Excellent workability.
- Can be used with water jetting surface preparation.
- Compatible with well-designed cathodic protection system.

Physical properties.

Colour Gray, (other colors available on request)

Texture Semi-gloss

Mixing and application Information

Number of components	Two
Mixing ratio	By Volume, base to hardener: 75 / 25
Specific gravity	Approx. 1.45 g/ml
Volume solids	80±2% Tested acc. ASTM D 2369
VOC	Approx. 194 g/liter
Flashpoint	>25°C
spray	Airless spray Recommended Pressure at nozzle: 180 - 250 bar. Nozzle size: 0.41 - 0.58 mm. Spray angle: 40 - 80 degrees. Thinning Ratio: 0 - 5%.
	Convention Air spray Thinning Ratio: 0 - 10%.
Brush	Suitable for stripe coat and touch up. Thinning Ratio: 0 - 10%
Roller	Suitable for stripe coat and touch up. Thinning Ratio: 0 - 10%.
Thinner/Cleaner	SAM Thinner No. 1 Thinning should only be added after the two components have been thoroughly mixed.
Pot life	90 min at 25 C°

Recommended film thickness range

Dry film thickness per coat (µm)	100 – 300 µm	ASTM D1186
Wet film thickness per coat (µm)	125 – 375 µm	ASTM D1212
Theoretical spreading rate (m ² /L)	8 - 2.6 m ² /L	

Sam mastic 80



Surface Preparation

Blast Cleaning

- Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion,
- Surface shall be treated in accordance with ISO, ASTM or SSPC standards.
- The abrasives shall be free from oil, grease, moisture, chloride contamination, etc. and comply with ISO 8504-2 and SSPC AB1.
- The surface roughness shall be complied with ISO 8503 and ASTM D4417 with roughness between 40µm: 70µm.

	minimum	Recommended
Carbon steel	ISO 8501-1 Sa 2, SSPC-SP6	ISO 8501-1 Sa 2½, SSPC-SP10.

Power Tool Cleaning

- The Surfaces must be clean, dry and free from oil and other contamination.
- Surfaces shall be treated in accordance with ISO 8504-3.
- Power-tool cleaning to min. St 2, SSPC-SP2, and St 3, SSPC-SP3 is preferred.
- In case of touch up, feathering the coated surface "**decreasing the edge thickness of a coat film**".

Water Jetting

- Water jetting in accordance with ISO 8501-4 and SSPC
- Flash rust degree is recommended to not exceed M (medium) and preferred to be L (light).

	Recommended
Atmospheric	Wa 2 or SSPC-WJ3.
Immersion	Wa 2.5 or SSPC-WJ2.

Coated Substrates

- The surface shall be papered to paint in accordance with ISO 8504, ISO12944-4 and ASTM D3276
- All surfaces must be clean, dry and free from contamination.
- For aged coated substrates, a fine abrasive should be utilized to roughen the surface to ensure coating adhesion.
- It is important to check that the selected paint system is compatible with the coated substrates before application.

Sam mastic 80



Drying and recoating information

Substrate temperature	10°C	23°C	30°C	
Touch dry	5 Hours	3 Hour	2 Hour	ASTM D 1640
Dry to handle	24 Hours	12 Hours	10 Hours	
Full cure	8 Days	7 Days	7 Days	
Dry to recoat	Min.	24 Hours	15 Hours	
	Max	Indefinite	Indefinite	

The drying and curing periods are established by subjecting the product to controlled temperatures and a relative humidity level that does not exceed 85%, and at average DFT range for the product.

Application conditions

- Avoid the formation of moisture on the surface, it is recommended that the temperature of the substrate remains at least 3°C higher than the dew point of the surrounding air, during painting process and until hard dry of the paint. It is important to take measurements of the temperature and relative humidity in the area surrounding the substrate according to ISO 8502-4.
- It is recommended to not exceed the surface temperature of approximately 45°C, as this can lead to the formation of dry-spray, pinholes, and sagging.
- For optimal results, it is important to mix the product thoroughly, making sure to combine the base and hardener in the recommended ratio.
- Thinning should only be added after the two components have been thoroughly mixed.
- To achieve the best results, it is advised to follow the product's TDS recommendations for thinning. Over-thinning the product can cause sagging and may also result in a weaker paint film.
- When working in small, cramped, confined spaces, it is important to ensure sufficient ventilation during both application and drying time.
- It is important to monitor the temperature of the paint, as it can impact its viscosity. To achieve the desired film thickness, it may be necessary to control thinning in order to reach the appropriate viscosity, for additional information, please get in touch with your Local SAMCO office.

Sam mastic 80



Safety Precautions

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes.
- Avoid inhalation of spray mist, it is important to take appropriate precautions. Skin contact should also be avoided, and any spills should be promptly cleaned up using soap, water, and a suitable cleanser. If the product comes into contact with the eyes, they should be thoroughly flushed with water and medical attention should be sought immediately.
- To ensure safe handling and use, please follow the guidelines below:
 - Wear appropriate personal protective equipment, such as gloves, eye protection, and respiratory protection, when handling or using this product.
 - Avoid direct skin contact and inhalation of dust, mist, or vapor.
 - If skin contact occurs, immediately wash the affected area with soap and water.
 - If the product comes into contact with the eyes, flush them thoroughly with water and seek medical attention immediately.
 - Use this product in a well-ventilated area to minimize the risk of inhalation.
 - Store the product in a cool, dry place, away from sources of heat or ignition.
 - Keep the product out of reach of children and animals.
 - Follow all applicable regulations and guidelines for handling, transportation, and disposal of this product.

Storage and shelf life

Ensure compliance with national regulations, proper storage guidelines must be followed for the product. The cans should be stored in a well-ventilated area that is dry, cool, and kept away from any heat or ignition sources. It is important to ensure that the cans are tightly closed at all times to maintain safety.

Disclaimer

All information in this document has been prepared to the best of SAMCO's knowledge, based on laboratory testing and practical experience to ensure good workmanship. However, the responsibility for executing the work stays with the applicator/ contractor/sub-contractor. SAMCO products are used under conditions beyond SAMCO's control. Users should always consult SAMCO for specific guidance on the general suitability of this product for their needs and specific application practices. SAMCO reserves the right to change the given data without further notice.