

Sam Epoxy Ester Finish

Product description.

A gloss, One-component, Epoxy ester finish coat.

Characteristics

- Good resistance to atmospheric exposure conditions.
- Excellent chemical resistant.
- For marine and Industrial environment
- For Interior and Exterior use.
- Excellent color and gloss retention.
- Non-yellowing, good UV resistance.
- Applied on SAMCO Epoxy systems or SAMCO Alkyd primers.
- Excellent workability

Physical properties.

Colour RAL colour standard

Texture Gloss

Mixing and application Information

Number of components	One
Specific gravity	Approx. 1.25 g/ml
Volume solids	45±2% Tested acc. ASTM D 2369
VOC	Approx. 500 g/l
Flash point	>24°C
Spray	Airless spray Recommended Pressure at nozzle: 120 - 150 bar. Nozzle size: 0.38 – 0.53mm. Spray angle: 40 - 80 degrees. Thinning Ratio: 0 - 5%.
Brush	Convention Air spray Thinning Ratio: 0 - 10%. Suitable for stripe coat and touch up.
Roller	Thinning Ratio: 0 - 10%. Suitable for stripe coat and touch up.
Thinner/Cleaner	Thinning Ratio: 0 - 10%. SAM Thinner No. 3

Recommended film thickness range

Dry film thickness per coat (µm)	30 – 50 µm	ASTM D1186
Wet film thickness per coat (µm)	66 – 111 µm	ASTM D1212
Theoretical spreading rate (m ² /L)	15 – 9 m ² /L	

Sam Epoxy Ester Finish

Surface Preparation

Coated substrates

- The surface shall be papered to paint in accordance with ISO 8504, ISO12944-4 and ASTM D3276
- All surfaces should be clean, dry and free from contamination.
- For aged coated substrates, a fine abrasive should be utilized to roughen the surface to ensure coating adhesion.
- It is important to check that the selected paint system is compatible with the coated substrates before application.

Drying and recoating information

Substrate temperature	10°C	23°C	30°C		
Touch dry	9 Hours	3 Hour	1 Hour	ASTM D 1640	
Dry to handle	15 Hours	9 Hours	3 Hours		
Full cure	7 Days	7 Days	5 Days		
Dry to recoat	Min.	10 Hours	12 Hours		8 Hours
	Max	Indefinite	Indefinite		Indefinite

The drying and curing periods are established by subjecting the product to controlled temperatures and a relative humidity level that does not exceed 85%, and at average DFT range for the product.

Application conditions

- Avoid the formation of moisture on the surface, it is recommended that the temperature of the substrate remains at least 3°C higher than the dew point of the surrounding air, during painting process and until hard dry of the paint. It is important to take measurements of the temperature and relative humidity in the area surrounding the substrate according to ISO 8502-4.
- It is recommended to not exceed the surface temperature of approximately 45°C, as this can lead to the formation of dry-spray, pinholes, and sagging.
- To achieve the best results, it is advised to follow the product's TDS recommendations for thinning. Over-thinning the product can cause sagging and may also result in a weaker paint film.
- When working in small, cramped, confined spaces, it is important to ensure sufficient ventilation during both application and drying time.
- It is important to monitor the temperature of the paint, as it can impact its viscosity. To achieve the desired film thickness, it may be necessary to control thinning in order to reach the appropriate viscosity, for additional information, please get in touch with your Local SAMCO office.

Sam Epoxy Ester Finish

Safety Precautions

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes.
- Avoid inhalation of spray mist, it is important to take appropriate precautions. Skin contact should also be avoided, and any spills should be promptly cleaned up using soap, water, and a suitable cleanser. If the product comes into contact with the eyes, they should be thoroughly flushed with water and medical attention should be sought immediately.
- To ensure safe handling and use, please follow the guidelines below:
 - Wear appropriate personal protective equipment, such as gloves, eye protection, and respiratory protection, when handling or using this product.
 - Avoid direct skin contact and inhalation of dust, mist, or vapor.
 - If skin contact occurs, immediately wash the affected area with soap and water.
 - If the product comes into contact with the eyes, flush them thoroughly with water and seek medical attention immediately.
 - Use this product in a well-ventilated area to minimize the risk of inhalation.
 - Store the product in a cool, dry place, away from sources of heat or ignition.
 - Keep the product out of reach of children and animals.
 - Follow all applicable regulations and guidelines for handling, transportation, and disposal of this product.

Storage and shelf life

Ensure compliance with national regulations, proper storage guidelines must be followed for the product. The cans should be stored in a well-ventilated area that is dry, cool, and kept away from any heat or ignition sources. It is important to ensure that the cans are tightly closed at all times to maintain safety.

Disclaimer

All information in this document has been prepared to the best of SAMCO's knowledge, based on laboratory testing and practical experience to ensure good workmanship. However, the responsibility for executing the work stays with the applicator/ contractor/sub-contractor. SAMCO products are used under conditions beyond SAMCO's control. Users should always consult SAMCO for specific guidance on the general suitability of this product for their needs and specific application practices. SAMCO reserves the right to change the given data without further notice.