

Sam Epoxy primer 65

Product description.

A two-component, polyamide-cured epoxy Primer with excellent anticorrosive properties.

Characteristics

- Good abrasion and impact resistance.
- Designed to be used in industrial and marine environment.
- Designed to be used over Carbon steel, Stainless steel and galvanized steel.
- Designed to be used as a holding primer that can be recoated after a period of time.
- Can be recoated with most mid and high build SAMCO Epoxies.
- Compatible with well-designed cathodic protection system.

Physical properties.

Colour Red brown, (specific colours)

Texture Flat

Mixing and application Information

| | |
|----------------------|---|
| Number of components | Two |
| Mixing ratio | By Volume, base to hardener: 80 / 20 |
| Specific gravity | Approx. 1.35 g/ml |
| Volume solids | 65±2% Tested acc. ASTM D 2369 |
| VOC | Approx. 300 g/liter |
| Flashpoint | >25°C |
| spray | Airless spray Recommended Pressure at nozzle: 180 - 250 bar. Nozzle size: 0.38 - 0.53 mm.. Spray angle: 40 - 80 degrees. Thinning Ratio: 0 - 5%. |
| | Convention Air spray Thinning Ratio: 0 - 10%. |
| Brush | Suitable for stripe coat and touch up. Thinning Ratio: 0 - 10% |
| Roller | Suitable for stripe coat and touch up. Thinning Ratio: 0 - 10%. |
| Thinner/Cleaner | SAM Thinner No. 1 Thinning should only be added after the two components have been thoroughly mixed. |
| Pot life | 3 Hours at 25 C° |

Recommended film thickness range

| | | |
|--|----------------------------|------------|
| Dry film thickness per coat (µm) | 50 – 100 µm | ASTM D1186 |
| Wet film thickness per coat (µm) | 77 – 154 µm | ASTM D1212 |
| Theoretical spreading rate (m ² /L) | 13 – 6.5 m ² /L | |

Sam Epoxy primer 65

Surface Preparation Carbon Steel.

Blast Cleaning

- Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.
- Surface shall be treated in accordance with ISO, ASTM or SSPC standards.
- The abrasives shall be free from oil, grease, moisture, chloride contamination, etc. and comply with ISO 8504-2 and SSPC AB1.
- The surface roughness shall be complied with ISO 8503 and ASTM D4417 with roughness between 40µm: 70µm.

| | |
|--------------|------------------------------|
| | Recommended |
| Carbon steel | ISO 8501-1 Sa 2½, SSPC-SP10. |

Power Tool Cleaning

- The Surfaces must be clean, dry and free from oil and other contamination.
- For Repair and Touch up only.
- Surfaces shall be treated in accordance with ISO 8504-3.
- Power-tool cleaning to recommended degree St 3, SSPC-SP3.
- Feathering the coated surface **"decreasing the edge thickness of a coat film"**.

Stainless Steel.

- The Surfaces must be clean, dry and free from oil and other contamination.
- The surfaces shall be treated in accordance with ISO 8504:2007, ISO 12944-4: 1998
- The surface shall be cleaned by light blasting using a fine non-iron abrasive.
- The abrasives shall be free from oil, grease, moisture, chloride contamination, etc. and comply with ISO 8504-2 and SSPC AB1.
- The surface roughness shall be complied with ISO 8503 and ASTM D4417 with roughness between 20µm: 30µm.

Galvanized steel

- The Surfaces must be clean, dry and free from oil and other contamination.
- The surfaces shall be treated in accordance with ASTM D6386-16
- The "white rust" and loose patina corrosion products shall be removed by pressurized fresh water cleaning or light blast cleaning.
- The surface shall be cleaned by light blasting using a fine non-iron abrasive.
- The abrasives shall be free from oil, grease, moisture, chloride contamination, etc. and comply with ISO 8504-2 and SSPC AB1.
- The surface roughness shall be complied with ISO 8503 and ASTM D4417 with roughness between 20µm: 30µm.

Sam Epoxy primer 65

Drying and recoating information

| Substrate temperature | 10°C | 23°C | 30°C | ASTM D 1640 |
|-----------------------|----------|------------|------------|-------------|
| Touch dry | 3 Hours | 2 Hour | 1 Hour | |
| Dry to handle | 10 Hours | 5 Hours | 3 Hours | |
| Full cure | 10 Days | 7 Days | 5 Days | |
| Dry to recoat | Min. | 15 Hours | 12 Hours | 10 Hours |
| | Max | Indefinite | Indefinite | Indefinite |

The drying and curing periods are established by subjecting the product to controlled temperatures and a relative humidity level that does not exceed 85%, and at average DFT range for the product.

Application conditions

- Avoid the formation of moisture on the surface, it is recommended that the temperature of the substrate remains at least 3°C higher than the dew point of the surrounding air, during painting process and until hard dry of the paint. It is important to take measurements of the temperature and relative humidity in the area surrounding the substrate according to ISO 8502-4.
- It is recommended to not exceed the surface temperature of approximately 45°C, as this can lead to the formation of dry-spray, pinholes, and sagging.
- For optimal results, it is important to mix the product thoroughly, making sure to combine the base and hardener in the recommended ratio.
- Thinning should only be added after the two components have been thoroughly mixed.
- To achieve the best results, it is advised to follow the product's TDS recommendations for thinning. Over-thinning the product can cause sagging and may also result in a weaker paint film.
- When working in small, cramped, confined spaces, it is important to ensure sufficient ventilation during both application and drying time.
- It is important to monitor the temperature of the paint, as it can impact its viscosity. To achieve the desired film thickness, it may be necessary to control thinning in order to reach the appropriate viscosity, for additional information, please get in touch with your Local SAMCO office.

Sam Epoxy primer 65

Safety Precautions

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes.
- Avoid inhalation of spray mist, it is important to take appropriate precautions. Skin contact should also be avoided, and any spills should be promptly cleaned up using soap, water, and a suitable cleanser. If the product comes into contact with the eyes, they should be thoroughly flushed with water and medical attention should be sought immediately.
- To ensure safe handling and use, please follow the guidelines below:
 - Wear appropriate personal protective equipment, such as gloves, eye protection, and respiratory protection, when handling or using this product.
 - Avoid direct skin contact and inhalation of dust, mist, or vapor.
 - If skin contact occurs, immediately wash the affected area with soap and water.
 - If the product comes into contact with the eyes, flush them thoroughly with water and seek medical attention immediately.
 - Use this product in a well-ventilated area to minimize the risk of inhalation.
 - Store the product in a cool, dry place, away from sources of heat or ignition.
 - Keep the product out of reach of children and animals.
 - Follow all applicable regulations and guidelines for handling, transportation, and disposal of this product.

Storage and shelf life

Ensure compliance with national regulations, proper storage guidelines must be followed for the product. The cans should be stored in a well-ventilated area that is dry, cool, and kept away from any heat or ignition sources. It is important to ensure that the cans are tightly closed at all times to maintain safety.

Disclaimer

All information in this document has been prepared to the best of SAMCO's knowledge, based on laboratory testing and practical experience to ensure good workmanship. However, the responsibility for executing the work stays with the applicator/ contractor/sub-contractor. SAMCO products are used under conditions beyond SAMCO's control. Users should always consult SAMCO for specific guidance on the general suitability of this product for their needs and specific application practices. SAMCO reserves the right to change the given data without further notice.